



S C H E D A T E C N I C A

ForeFront Film

3.F

10μ



3.F AUTOMATICO 10 MY

RAW MATERIAL: LLDPE
PROCESS: CAST
THICKNESS: 10 MY

PROPERTIES		UNIT	TOLERANCE	VALUE	TESTMETHOD
THICKNESS		MICRON	± 2%	10	UNI 8516
ROLLWEIGHT		KG	± 2%	17,5	
PALLETWEIGHT		KG	± 2%	787,5	
ROLLS/PALLET				45	
WIDTH		MM	+5	500	
CORE Ø		MM	± 1	76	
ROLL Ø		MM	± 2%	238	
FORCE/MM ²	MD TD	N/ MM ²		21 13	ASTM D 882
FORCE MAX.	MD TD	N		9 5	ASTM D 882
ELONGATION	MD TD	%		400 547	ASTM D 882
DART IMPACT		GR.		150	ASTM D 1709