



ForeFront Film

3.F

17 μ 

3.F AUTOMATICO 17 MY

RAW MATERIAL: LLDPE
 PROCESS: CAST
 THICKNESS: 17

PROPERTIES	UNIT	TOLERANCE	VALUE	TESTMETHOD
THICKNESS	MICRON	$\pm 2\%$	17	UNI 8516
ROLLWEIGHT	KG	$\pm 2\%$	41	
PALLETWEIGHT	KG	$\pm 2\%$	492	
ROLLS/PALLET			12	
WIDTH	MM	+5	470	
CORE \varnothing	MM	± 1	76	
ROLL \varnothing	MM	$\pm 2\%$	392	
FORCE/MM ²	MD TD	N/ MM ²	37 22	ASTM D 882
FORCE MAX.	MD TD	N	18 8	ASTM D 882
ELONGATION	MD TD	%	610 830	ASTM D 882
DART IMPACT		GR.	420	ASTM D 1709